

5155C3

55 MELT FLOW CLARIFIED RANDOM COPOLYMER FOR INJECTION MOLDING

Product Description and Applications:

Pinnacle Polymers Polypropylene 5155C3 is made via UNIPOL™ PP technology, which utilizes gas-phase fluidized bed reactors with a high activity catalyst system to ensure uniform physical properties and lot-to-lot consistency.

This product is intended for injection molding applications that require high melt flow, fast cycle time, enhanced processability and excellent clarity. This product also has improved impact resistance and a new generation clarifier.

Features:

The 5155C3 product provides:

- Improved FDA food contact status
- New generation clarifier
- Improved color
- Excellent impact resistance
- High melt flow, excellent processability

Typical Properties

Property	Traditional Units	SI Units	ASTM Test
Melt Flow Rate	55 g/10 min.	55 g/10 min.	D1238
Density at 23°C	0.9 g/cm ³	900 kg/m ³	D1505
Shrinkage	0.015 in/in	0.015 mm/mm	D955
Heat Deflection Temperature at 0.455 MPa (66psi)	163°F	73°C	D648
Tensile yield strength, at 51 mm/min	3900 psi	26.9 MPa	D638
Yield elongation, at 51 mm/min	12%	12%	D638
Flexural modulus (1% secant) at 1.27 mm/min	145,000 psi	1000 MPa	D790A
Notched Izod impact strength, at 73°F/23°C	1.2 ft-lb/in	64 J/m	D256
% Yellowness Index	Less than -10	Less than -10	
Haze (1.27 mm plaque)	9%	9%	

FDA and SDS documents are available on our website at: <https://pinnaclepolymers.com/documents-datasheets/regulatory-documents>

UNIPOL is a trademark of Union Carbide Corporation

Technical data contained herein is furnished without fee or obligation, and is given and accepted at recipient's sole risk. Since conditions of use may vary and are beyond our control, Pinnacle Polymers makes no representation about and is not responsible or liable for the accuracy or reliability of data, nor for toxicological effects, industrial hygiene requirements, or other matters associated with particular application of any product described herein. Pinnacle Polymers disclaims any warranty, expressed or implied, regarding the information contained herein, including the implied warranty of merchantability of fitness for a particular purpose. .021826